

TECHNICAL DETAILS***COVERAGE RATE**

5.3 ft² per kg for each ±1/32" of depth
(0.5 m² per kg for each 1 mm of depth)

PACKAGING

5-kg cans
11 lbs. each

FORM/COLOR

Fluid
Gray

CATALYST CALCULATOR†**37-50°F (3-10°C)**

6 scoops
60 g

50-68°F (10-20°C)

4 scoops
40 g

68-95°F (20-35°C)

2 scoops
20 g

REACTION TIMES@68°F (20°C)

Pot Life: 20-30 minutes
Rainproof: 45 minutes
Fully Cured: 3 hours

FEATURES & BENEFITS

- Paste readies substrates for EZ Seal
- EZ Seal membranes are monolithic, flexible and seamless
- Ideal for access-restricted areas and difficult waterproofing conditions

* Gross yield/container is approximate. See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

† Measures amount of EZ Seal Catalyst required per 1 kg of resin. Scoop provided with catalyst measures 10 g. In most situations, 2 scoops of catalyst per kg of resin is satisfactory.

EZ SEAL PASTE

PRODUCT USE

EZ Seal Paste is a high-performance, two-component, rapid-curing paste used for leveling, patching and repairs to substrates prior to application of EZ Seal Non-Fibered and Fibered Resins. Malarkey Roofing Products® EZ Seal System is waterproof, flexible, self-adhering, and ideal for access-restricted and difficult waterproofing conditions. EZ Seal conforms and bonds directly to the substrate, eliminates the need for caulk and pitch pans, and is virtually maintenance-free.

COMPOSITION & MATERIALS

EZ Seal Paste is a flexible, acrylic, thixotropic resin. EZ Seal Paste is activated with Malarkey Roofing Products® EZ Seal Catalyst Powder (790-2).

APPLICATION/INSTALLATION

Before adding catalyst, thoroughly stir entire drum of EZ Seal Paste, and portion-off into a second container for batch mixing. Add pre-measured catalyst, mix, and stir again. Catalyze only the amount of material you can use within 20-30 minutes. Apply to substrates prepared as specified in the EZ Seal Application Instructions. Contact Malarkey's Technical Services Department for details.

PRECAUTIONS

EZ Seal Paste is harmful by inhalation and irritating to eyes and skin. Vapors may form an explosive mixture with air so keep away from heat, flame and ignition sources. To ensure safety when handling, the user should wear appropriate PPE, including respirator in enclosed spaces. Wash thoroughly after handling. Consult SDS for complete details.

EZ Seal Paste shall be stored in its original container with adequate ventilation. When not in use, keep container closed in a cool, dry location. In case of spill, absorb with liquid-binding material, collect, and dispose of waste in accordance with federal, state and local regulations. Uncured product must be catalyzed before disposal.

EMERGENCY INFORMATION:

For Chemical Emergency, Spill Leak, Fire Exposure or Accident
Call CHEMTREC Day or Night; in North America 800-424-9300

Substrates must be clean, dry, free of surface moisture, oil, grease, contaminants, and any other material or condition which would adversely effect bonding of EZ Seal to the substrate.

WARRANTY

Malarkey Roofing Products® offers various warranties to meet specific requirements. Contact your roofer, local distribution center or Malarkey for full details. See below for TECHNICAL ASSISTANCE contact information.

EZ Seal and other Malarkey products are available throughout North America and Pacific Rim countries.

Visit WWW.MALARKEYROOFING.COM for additional product information and availability.

Note: Malarkey Roofing Products® (Malarkey) inventory SKU number for this product: 755-5 EZ Seal Paste

TECHNICAL ASSISTANCE:

Malarkey has technical services assistance available.
Contact Malarkey for details:
Call weekdays 7:00 am to 5:00 pm PST,
at 800.545.1191 or 503.283.1191.
technicalinquiries@malarkeyroofing.com

CORPORATE OFFICE:

3131 N. Columbia Blvd. Telephone: 503.283.1191
Portland, OR 97217-7472 or 800.545.1191
P.O. Box 17217 Fax: 503.289.7644
Portland, OR 97217-0217

Effective 1/16
Supersedes all previously published data
Check for most current version
on our website.